

## Product Data Sheet

### EcoSoya Q220

#### Product Description

Soy wax.

#### Technical Properties

Analysis	Typical	Method
Mettler Drop Point	117F (47.2C)	AOCS Cc 18-80
Congealing Point	109F (42.8C)	ASTM D 938-60
Needle Penetration (1/10 mm)	45	ASTM D 1321-65
Color, Red	3.5	AOCS Cc 13b-45

#### Suggested Applications/Possible Uses

Container Candles, Pillar Candles, Molded Candles, Tarts, Melts and other applications.

#### Shelf Life

##### Solid Wax

No determined shelf life if stored under proper conditions.

##### Liquid Wax

One to two weeks under proper storage conditions.

#### Shipping and Storage

##### Solid Wax

Store in a cool, dry location away from direct heat, sunlight, and moisture. Temporary hot or cold temperature extremes have no adverse effect. EcoSoya waxes may be used frozen and, if partially melted, allow to cool, and re-solidify before use.

##### Liquid Wax

Liquid wax should be shipped under a nitrogen blanket and have no contact with brass or copper. For storage, wax should be kept just above the melting point with no agitation, under nitrogen blanket, and have no contact with brass or copper.

**EcoSoya Brands, LLC | [www.ecosoyabrands.com](http://www.ecosoyabrands.com) | Tel: 1-865-690-3183**